

SUMITOMO CHEMICAL ASIA
Product Data Sheet
SUMITOMO POLYETHYLENE LLDPE
FS250B

Linear Low Density, Cast and Blown Film

Applications	For cast stretch film, lamination film, wires and cable, general purpose cast and blown film applications.
Characteristics	High strength, tough, and easy processability transparent cast film. Also used for wire and cable and high strength blown film, non-slip with excellent processability. For higher transparency, blending with LDPE is recommended.
Typical Processing Conditions	Cast extrusion temperature : 200°C - 280°C Blown extrusion temperature : 160°C - 200°C, blow-up ratio 2 - 3

Typical Properties

Physical		Value	Unit	Method
Melt Index	2.16kg	2.2	g/10min	ASTM D1238
Density		0.921	g/cm ³	ASTM D792-A
Thermal		Value	Unit	Method
Melting Temperature		122	°C	DSC
Film		Value	Unit	Method
Thickness		20, cast 30, blown	µm	
Tensile Strength at Break	MD / TD	40 / 30	MPa	ASTM D882
Tensile Elongation at Break	MD / TD	670 / 850	%	ASTM D882
Tensile Modulus, 1% Secant	MD / TD	160 / 155	MPa	ASTM D882
Elmendorf Tear Strength	MD / TD	70 / 215	gf	ASTM D1922
Coefficient of Friction, Exterior	µ _s / µ _k	NA / NA	>0.51 / ND	ASTM D1894
Dart Drop Impact		65 90	g	ASTM D1709
Haze		0.7	%	ASTM D1003
Gloss	45°	150 50		ASTM D2457
Other		Value	Unit	Method
Flamability		HB		UL94

The values shown are typical values measured on the product and are not to be considered as guaranteed specifications, actual test results may vary
 Test pieces preparation condition : as per ASTM D4976
 Cast film processing condition : extruder ø55mm, die width 600mm, die gap 1.2mm, temperature 280°C, chill roll temperature 30°C, output 50kg/hr, line speed 75m/min, thickness 20µm
 Blown film processing condition : extruder ø55mm, die ø125mm, die gap 2.0mm, temperature 200°C, output 30kg/hr, blow-up ratio 2.0, thickness 30µm

 SUMITOMO CHEMICAL ASIA**Manufacturer**

FS250B is manufactured in Saudi Arabia by Rabigh Refining & Petrochemical Co. (Petro Rabigh). Petro Rabigh is an ISO 9001, ISO 14001, and ISO 45001 certified company.

Regulatory Compliances

Unmodified FS250B complies with the requirements of,

- US FDA Regulation 21 CFR 177.1520 and its amendments
- Regulation (EC) 1935/2004/EC (Framework), EU Commission Regulation 10/2011 (PIM), Commission Regulation (EC) No.2023/2006 (GMP), and their respective amendments

Please contact your nearest SCA representative for more information.

Restriction of Hazardous Substances

The substances regulated under EU Directive 2011/65/EC, and its amendments, on RoHS in electrical and electronic equipment are not used in the manufacturing process, and are therefore not expected to be present in the product.

Storage and Handling

FS250B is supplied in 25kg bags or in bulk containers. It is advisable to store in a well-ventilated storage facility, protected from rain, direct exposure to sunlight, temperature, and dust.

Moisture may accumulate inside the packaging if there is a significant fluctuation in ambient temperature and high relative humidity. If this occurs, customer is strongly advised to dry the resin prior to use. Direct exposure to sunlight and excessive ambient temperature may affect the properties, appearance, and odour characteristic of the resin.

It is recommended to process FS250B within 6 months upon receipt.

Please refer to the Safety Data Sheet (SDS) for information regarding industrial health and safety issues.

Disposal and the Environment

SCA prioritises environmental management in all our operations in responsibility and respect towards the community and the environment.

Unmodified FS250B is readily recyclable, both for reuse via reprocessing and for energy reclamation through incineration. If disposed in landfills, our products, which are inert materials, do not pose pollution risks since they do not generate gaseous or liquid emissions.

Office Locations**SUMITOMO CHEMICAL ASIA PTE LTD**

3 Fraser Street, #07-28 DUO Tower, SINGAPORE 189352

Phone +65 6303 5188

Fax +65 6298 9621

Web Site www.sumitomo-chem.com.sg

SUMIKA PLASTICS AND CHEMICALS TRADING (SHANGHAI) CO., LTD.

1607, Ascendas Plaza, 333 Tian Yao Qiao Road, Xu Hui District, Shanghai, CHINA 200030

Phone +86 21 6448 2255

Fax +86 21 6407 7365

SUMIKA PLASTICS AND CHEMICALS TRADING (SHANGHAI) CO., LTD., GUANGZHOU BRANCH

Room 6404, Office Building, CITIC Plaza, No.233, North Tianhe Road, Guangzhou City, CHINA 510613

Phone +86 20 3877 3577

Fax +86 20 3877 3511

SUMITOMO CHEMICAL EUROPE S.A./N.V.

Woluwelaan, 57, B-1830 Machelen, BELGIUM

Phone +32 2 251 0650

Fax +32 2 251 2991

Web Site sumitomochemicaleurope.eu

SUMITOMO CHEMICAL EUROPE N.V.

Turkey Liaison Office, Barbaros Mah. Cigdem Sok. No:1, Agaoglu My Office K:10, D:44-45, 34746 Bati Atasehir, Istanbul, TURKEY

Phone +90 216 680 3334

Fax +90 216 680 1012

Disclaimer

All information contained in this document is provided in good faith and its sole purpose is to provide information regarding SCA's polymer products. This product catalogue is provided on an "as is" basis. SCA makes no representation, warranty, express or implied and assumes no liability as to the accuracy or completeness of any of the information contained in this product catalogue. The values shown are purely values measured on the product and are not to be considered as guaranteed specifications. Any information on this product catalogue should not be considered as a recommendation. Customer is responsible to ensure that SCA materials, whether used alone or mix with other materials, are suitable for the intended application. SCA expressly disclaims for any and all liability, including direct and indirect loss, consequential loss or damages based on or relating to the use or errors of and omissions of such information in this product catalogue. Information contained herein is NOT intended to announce product availability anywhere in the world. Please contact your nearest SCA representative for more detailed information.