


TotalEnergies

TotalEnergies Petrochemicals & Refining USA, Inc.
Polymers Americas

Polypropylene 4481WZ

Technical Data Sheet
Polypropylene – Impact Copolymer
Produced in the United States

Description

Polypropylene 4481WZ is a nucleated impact copolymer with a Melt Flow of 4.0 g/10min

4481WZ is characterized by a good stiffness/impact balance coupled with high creep resistance. This grade has been developed for sheet extrusion and thermoforming applications requiring good mechanical properties and aesthetic appearance.

4481WZ has been specially formulated with an additive for excellent antistatic properties as well as good surface appearance and mold release.

Characteristics

	Method	Unit	Typical Value
Rheological Properties			
Melt Flow	ASTM D-1238	g/10 min	4.0
Mechanical Properties			
Tensile, Strength at Yield	ASTM D-638	psi (MPa)	4,900 (34)
Elongation at Yield	ASTM D-638	%	7
Flexural Modulus	D-790	psi (MPa)	250,000 (1,725)
Izod (Notched) @ 23°C	ASTM D-256	ft.-lbs/in.	2.5 (135)
Thermal Properties⁽¹⁾			
Melting Range	TOTAL Polypropylene Method	°F (°C)	320-329 (160-165)
Heat Deflection	ASTM D-648	°F (°C)	243 (117)
Other Physical Properties			
Density	ASTM D-1505	g/cm ³	0.905

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

Rev: Sept 2021

TOTALENERGIES PETROCHEMICALS & REFINING USA, INC.
POLYMERS AMERICAS
1201 Louisiana Street
Suite 1800
Houston, TX 77002
www.polymers.totalenergies.com

TECHNICAL CENTER
P.O. Box 1200
Deer Park, Texas 77536
Phone: 281-884-7500

1-800-344-3462

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TotalEnergies products must be guided by the users own methods for selection of proper formulation. TotalEnergies Petrochemicals & Refining USA Inc. disclaims any responsibility for misuse or misapplication of its products. TotalEnergies MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TotalEnergies' liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.