



## Polypropylene 6575

Technical Data Sheet  
Polypropylene – Random Copolymer  
Produced in the United States

TotalEnergies Petrochemicals & Refining USA, Inc.  
Polymers Americas

### Description

**Polypropylene 6575:** Low catalyst residuals results in improved color stability.

**Clarity/Impact:** 6575 improves its clarity and resiliency over conventional homopolymer films.

**FDA:** 6575 complies with all applicable FDA regulations for food contact applications.

**Recommended Applications:** 6575 is recommended for use in manufacture of packaging films that require improved optical and resiliency or special surface attributes.

**Processing:** 6575 resin processes with typical melt temperatures of 450°F-525°F (232°C-274°C).

### Characteristics

|                                                       | Method    | Unit                   | Typical Value |
|-------------------------------------------------------|-----------|------------------------|---------------|
| <b>Rheological Properties</b>                         |           |                        |               |
| Melt Flow                                             | D-1238    | g/10 min               | 8.0           |
| <b>Film Properties, Non-Oriented<sup>(1)(3)</sup></b> |           |                        |               |
| Ultimate Tensile                                      | D-882     | psi (MPa)              | 7,000 (48)    |
| Elongation at Break                                   | D-882     | %                      | 500           |
| 1% Secant Modulus                                     | D-882     | psi (MPa)              | 100,000 (689) |
| WVTR @ 100°F, 90% RH                                  | F-1249-90 | g/100 sq-in/24 hrs/mil | 0.7           |
| Haze                                                  | D-1003    | %                      | 2.0           |
| Gloss@ 45°                                            | D-2457    | %                      | 80            |
| Dart Impact (F50)                                     | D-1709    | g/mil                  | 35            |
| <b>Thermal Properties<sup>(1)(2)</sup></b>            |           |                        |               |
| Melting Point                                         | DSC       | °F (°C)                | 293 (145)     |
| <b>Other Physical Properties</b>                      |           |                        |               |
| Density                                               | D-792     | g/cc                   | 0.90          |

- (1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.  
(2) MP determined with a DSC-2 Differential Scanning Calorimeter. Test procedure available upon request.  
(3) Cast film, 2.0 mil

Rev: May 2022

TOTALENERGIES PETROCHEMICALS & REFINING USA, INC.  
POLYMERS AMERICAS  
1201 Louisiana Street  
Suite 1800  
Houston, TX 77002  
[www.polymers.totalenergies.com](http://www.polymers.totalenergies.com)

TECHNICAL CENTER  
P.O. Box 1200  
Deer Park, Texas 77536  
Phone: 281-884-7500

**1-800-344-3462**

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of TotalEnergies products must be guided by the users own methods for selection of proper formulation. TotalEnergies Petrochemicals & Refining USA Inc. disclaims any responsibility for misuse or misapplication of its products. TotalEnergies MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. TotalEnergies' liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.