



The Polyolefin Company (Singapore) Pte

Office : 150 Beach Road, #10-00 Gateway West, Singapore 189720
 Tel: (65) 6292 9622 Fax: (65) 6293 8890, (65) 6292 6595, (65) 6293 8891
 Plant : 401 Ayer Merbau Road, Singapore 628285
 Website: www.tpc.com.sg Co. Reg. No.:

COSMOPLENE® AX668

CHARACTERISTICS

COSMOPLENE AX668 is a high flow; high stiffness and high impact PP b copolymer manufactured by gas phase process licensed from Sumit Chemical Co. Japan.

APPLICATIONS

COSMOPLENE AX668 is suitable for thin gauge injection products such as and operation panel of washing machine and automotive parts.

COSMOPLENE AX668 is formulated with UV stabilizer and is good for outdoor applications.

PHYSICAL PROPERTIES

ITEM	UNIT	AX668	TEST METHOD
Melt Flow Rate	g/10 min	65	ASTM D123
Density	g/cm ³	0.90	ASTM D792
Tensile Strength at Yield	MPa	27.5	ASTM D638
Tensile Strength at Break	MPa	17.0	ASTM D638
Elongation at Break	%	50	ASTM D638
Flexural Modulus	MPa	1320	ASTM D790
Izod Impact (23°C)	J/m	65	ASTM D256
(-20°C)	J/m	40	ASTM D256
Rockwell Hardness	R scale	92	ASTM D785
HDT (0.45MPa)	°C	126	ASTM D648
Shrinkage MD/TD (2mm)	%	1.6/1.7	TPC METHOD
Weatherability (63°C)	Hr.	1,000	SWOM

INJECTION

Cylinder Temp (°C) : 190 - 230°C
 Mold Temp (°C) : 30-40°C
 Clamp Pressure (Kg/cm²) : 100
 Injection Pressure G (Kg/cm²) : 70

- The figures presented are typical laboratory averages, only for reference.
- The information is based on our current knowledge, is subjected to continuous updates and is intended to suggest/ recommend product applications and to provide typical data on the related properties. It should not therefore be construed as guaranteeing any specific property of the product. TPC makes no warranty of any kind, expressed or implied, regarding the accuracy of these data.