



The Polyolefin Company (Singapore) Pte

Office : 150 Beach Road, #10-00 Gateway West, Singapore 189720

Tel: (65) 6292 9622 Fax: (65) 6293 8890, (65) 6292 6595, (65) 6293

Plant : 401 Ayer Merbau Road, Singapore 628285

Website: www.tpc.com.sg

Co. Reg. No.:

COSMOPLENE[®] AZ564G

CHARACTERISTICS

COSMOPLENE AZ564G is a high impact PP copolymer manufactured by phase process licensed from Sumitomo Chemical Co. Japan.

COSMOPLENE AZ564G is high flow, high stiffness, high impact copoly grade.

APPLICATIONS

COSMOPLENE AZ564G is specially designed for industrial parts, automotive door trims and electrical appliances etc.

PHYSICAL PROPERTIES

ITEM	UNIT	AZ564G	TEST METHOD
Melt Flow Rate	g/10 min	38	ASTM D1238
Density	g/cm ³	0.90	ASTM D792
Tensile Strength at Yield	MPa	23.5	ASTM D638
Tensile Strength at Break	Mpa	15.0	ASTM D638
Elongation at Break	%	50	ASTM D638
Flexural Modulus	MPa	1150	ASTM D790
Izod Impact (23°C)	J/m	85	ASTM D256
(-20°C)	J/m	46	ASTM D256
Rockwell Hardness	R scale	86	ASTM D785
HDT (0.45MPa)	°C	122	ASTM D648
Shrinkage MD/TD (2mm)	%	1.5/1.7	TPC METHOD
Flammability (E108370)	-	HB	UL 94

INJECTION

Cylinder Temp (°C)	:	190 - 230
Mold Temp (°C)	:	30
Clamp Pressure (Kg/cm ²)	:	100
Injection Pressure G (Kg/cm ²)	:	70

- The figures presented are typical laboratory averages, only for reference.
- The information is based on our current knowledge, is subjected to continuous updates and is intended to suggest/ recommend product applications and to provide typical data on the related properties. The information should not therefore be construed as guaranteeing any specific property of the product. TPC makes no warranty of any kind, expressed or implied, for the use of the product.