



The Polyolefin Company (Singapore) Pte

Office : 150 Beach Road, #10-00 Gateway West, Singapore 189720

Tel: (65) 6292 9622 Fax: (65) 6293 8890, (65) 6292 6595, (65) 6293

Plant : 401 Ayer Merbau Road, Singapore 628285

Website: www.tpc.com.sg

Co. Reg. No.:

COSMOPLENE[®] FC9412G

CHARACTERISTICS

COSMOPLENE FC9412G is Polypropylene Random Copolymer specially designed for PP woven cloth coating with low coating temperature, high bond strength and small Neck in.

APPLICATIONS

Extrusion coating for PP woven bag, cloth/paper sandwich for Chemical cement bag.

FC9412G complies with U.S. FDA Regulation 21 CFR 177.1520 (C) 3.1a, as long as it is used unmodified and processed according to standard manufacturing practices in the industries.

Note : Direct food contact is subjected to the extraction provisions of the regulation on the finished contact article.

PHYSICAL PROPERTIES

ITEM	UNIT	FC9412G	TEST METHOD
Melt Flow Rate	g/10 mins	20	ASTM D1238
Density	g/cm ³	0.90	ASTM D792
Tensile Strength at break	MPa	29	ASTM D638
Elongation at break	%	840	ASTM D638
Stiffness	MPa	740	ASTM D747
Melting Point	°C	146	TPC METHOD

- The figures presented are typical laboratory averages, only for reference.
- The information is based on our current knowledge, is subjected to continuous updates and is intended to suggest/ recommend product applications and to provide typical data on the related properties. It should not therefore be construed as guaranteeing any specific property of the product. TPC makes no warranty of any kind, expressed or implied, regarding the accuracy of these data.