



The Polyolefin Company (Singapore) Pte.

Office : 150 Beach Road, #10-00 Gateway West, Singapore 189720

Tel: (65) 6292 9622 Fax: (65) 6293 8890, (65) 6292 6595, (65) 6293 2

Plant : 401 Ayer Merbau Road, Singapore 628285

Website: www.tpc.com.sg

Co. Reg. No.: 1

COSMOPLENE[®] FC9413P

CHARACTERISTICS

COSMOPLENE FC9413P is Polypropylene Random Copolymer specially designed for g transparency, low heat seal, higher stiffness and good adhesion with BOPP film.

APPLICATIONS

Extrusion coating on BOPP film for the packaging of snack food, instant noodle, candy a many others food packing which require clarity.

FC9413P complies with U.S. FDA Regulation 21 CFR 177.1520 (C) 3.1a, as long as used unmodified and processed according to standard manufacturing practices in industries.

Note : Direct food contact is subjected to the extraction provisions of the regulation on the finished food contact article.

PHYSICAL PROPERTIES

ITEM	UNIT	FC9413P	TEST METHO
Melt Flow Rate	g/10 mins	20	ASTM D1238
Density	g/cm ³	0.90	ASTM D792
Tensile Strength at break	MPa	37	ASTM D638
Elongation at break	%	980	ASTM D638
Stiffness	MPa	770	ASTM D747
Melting Point	°C	147	TPC METHO

Remarks:

- * Draw down property of FC9413P by itself have been confirmed at 300m/min with stable edges at resin stock temper 290°C for 15μ coating thickness.
- The figures presented are typical laboratory averages, only for reference.
- The information is based on our current knowledge, is subjected to continuous updates and is intended to sug recommend product applications and to provide typical data on the related properties. It should not therefore be consi as guaranteeing any specific property of the product. TPC makes no warranty of any kind, expressed or implied, rega the accuracy of these data.