



The Polyolefin Company (Singapore) Pte. Ltd.

Office : 150 Beach Road, #10-00 Gateway West, Singapore 189720

Tel: (65) 6292 9622 Fax: (65) 6293 8890, (65) 6292 6595, (65) 6293 2748

Plant : 401 Ayer Merbau Road, Singapore 628285

Website: www.tpc.com.sg

Co. Reg. No.: 198001666D

COSMOPLENE® FL7322

CHARACTERISTICS

COSMOPLENE FL7322 is Polypropylene Copolymer with higher Aluminum bonding strength, good appearance, good process stability and lower die deposit.

APPLICATIONS

COSMOPLENE FL7322 is designed for Aluminum metalized layer of cast film (M-CPP) application. **FL7322** contains anti-blocking agent only.

FL7322 complies with U.S. FDA Regulation 21 CFR 177.1520 (C) 3.1a, as long as it is used unmodified and processed according to standard manufacturing practices in the industries.

Note : Direct food contact is subjected to the extraction provisions of the regulation on the finished food contact article.

PHYSICAL PROPERTIES

ITEM	UNIT	FL7322	TEST METHOD
Melt Flow Rate	g/10 mins	10	ASTM D1238
Density	g/cm ³	0.90	ASTM D792
Tensile Strength at Break	MPa	37	ASTM D638
Elongation	%	890	ASTM D638
Stiffness	MPa	980	ASTM D747
Melting Point	°C	143	TPC METHOD

FILM PROPERTIES (30μ)

ITEM	UNIT	FL7322	TEST METHOD
Haze	%	2.4	ASTM D1003
Gloss	%	139	ASTM D2457
Young Modulus (MD) TD	MPa	650 640	TPC METHOD

Die temperature: 250°C, Chill roll temperature: 50°C

- The figures presented are typical laboratory averages, only for reference.
- The information is based on our current knowledge, is subjected to continuous updates and is intended to suggest/recommend product applications and to provide typical data on the related properties. It should not therefore be construed as guaranteeing any specific property of the product. TPC makes no warranty of any kind, expressed or implied, regarding the accuracy of these data.



Dec 2016

COSMOPLENE®
POLYPROPYLENE

COSMOTHENE®
LOW DENSITY POLYETHYLENE

COSMOTHENE® EVA
ETHYLENE VINYL
ACETATE COPOLYMER