



The Polyolefin Company (Singapore) Pte

Office : 150 Beach Road, #10-00 Gateway West, Singapore 189720

Tel: (65) 6292 9622 Fax: (65) 6293 8890, (65) 6292 6595, (65) 6293

Plant : 401 Ayer Merbau Road, Singapore 628285

Website: www.tpc.com.sg

Co. Reg. No.:

COSMOPLENE® FL7642

CHARACTERISTICS

COSMOPLENE FL7642 is Polypropylene Terpolymer product with good Aluminum adhesiveness, good process stability and low seal temperature.

APPLICATIONS

COSMOPLENE FL7642 is designed for heat sealing layer in Aluminum metalized cast film (MCP) application. **FL7642** contains antiblocking agent only.

FL7642 complies with U.S. FDA Regulation 21 CFR 177.1520 (C) 3.1a, as long as it is used unmodified and processed according to standard manufacturing practices in the industries.

Note : Direct food contact is subjected to the extraction provisions of the regulation on the finished contact article.

PHYSICAL PROPERTIES

ITEM	UNIT	FL7642	TEST METHOD
Melt Flow Rate	g/10 mins	7	ASTM D123
Density	g/cm ³	0.90	ASTM D792
Tensile Strength at break	MPa	45	ASTM D638
Elongation	%	880	ASTM D638
Stiffness	MPa	780	ASTM D747
Melting Point	°C	128	TPC METHOD

FILM PROPERTIES (30μ)

ITEM	UNIT	FL7642	TEST METHOD
Haze	%	2.5	ASTM D100
Gloss	%	140	ASTM D245
Young Modulus (MD) (TD)	MPa	650 640	TPC METHOD
Heat Seal Temperature	°C	116	TPC METHOD

Extrusion Temperature - 240°C, Chill Roll Temperature - 50°C

- The figures presented are typical laboratory averages, only for reference.
- The information is based on our current knowledge, is subjected to continuous updates and is intended to suggest/ recommend product applications and to provide typical data on the related properties. It should not therefore be construed as guaranteeing any specific property of the product. TPC makes no warranty of any kind, expressed or implied, regarding the accuracy of these data.