



The Polyolefin Company (Singapore) Pte. Ltd.

Office : 150 Beach Road, #10-00 Gateway West, Singapore 189720

Tel: (65) 6292 9622 Fax: (65) 6293 8890, (65) 6292 6595, (65) 6293 2748

Plant : 401 Ayer Merbau Road, Singapore 628285

Website: www.tpc.com.sg

Co. Reg. No.: 198001666D

COSMOPLENE® FS3031

CHARACTERISTICS

COSMOPLENE FS3031 is Polypropylene Homopolymer resin developed for Biaxially oriented films for dielectric applications used in capacitors.

COSMOPLENE FS3031 is a high purity resin with low ash content. It does not contain slip, antiblock, nucleating and antistatic additives.

APPLICATIONS

COSMOPLENE FS3031 is specially designed for biaxially oriented films for dielectrical films used in capacitors.

PHYSICAL PROPERTIES

ITEM	UNIT	FS3031	TEST METHOD
Melt Flow Rate	g/10 mins	3.4	ASTM D1238
Density	g/cm ³	0.90	ASTM D792
Melting Point	°C	168	TPC METHOD
Crystallization Point	°C	119	TPC METHOD
Isotactic index	%	98	TPC METHOD
Catalyst residue, Titanium	ppm	<1	TPC METHOD
Aluminium	ppm	<5	TPC METHOD
Chloride	ppm	<10	TPC METHOD
Total Ash content	ppm	<30	TPC METHOD

- The figures presented are typical laboratory averages, only for reference.
- The information is based on our current knowledge, is subjected to continuous updates and is intended to suggest/recommend product applications and to provide typical data on the related properties. It should not therefore be construed as guaranteeing any specific property of the product. TPC makes no warranty of any kind, expressed or implied, regarding the accuracy of these data.



Mar 2019

COSMOPLENE®
POLYPROPYLENE

COSMOTHENE®
LOW DENSITY POLYETHYLENE

COSMOTHENE® EVA
ETHYLENE VINYL
ACETATE COPOLYMER