



The Polyolefin Company (Singapore) Pte

Office : 150 Beach Road, #10-00 Gateway West, Singapore 189720

Tel: (65) 6292 9622 Fax: (65) 6293 8890, (65) 6292 6595, (65) 6293

Plant : 401 Ayer Merbau Road, Singapore 628285

Website: www.tpc.com.sg

Co. Reg. No.:

COSMOTHENE® EVA

CHARACTERISTICS

COSMOTHENE EVA is produced by the latest autoclave process technology licensed by Sumitomo Chemical Co. Japan.

COSMOTHENE EVA have good processability, tough, elastic, good ESCR good low temperature resistance.

APPLICATIONS

Mold wedge for sports shoe soles, cushioning materials and thermal insulation beach sandals etc.

PHYSICAL PROPERTIES (SHEET):

ITEM	TEST METHOD	UNIT	H2181	H2020	K32
Vinyl Acetate Content	TPC METHOD	Wt. %	18	15	2
Melt Flow Rate	ASTM D1238	G/10 min	2	1.5	3
Density	ASTM D792	g/cm ³	0.94	0.93	0.9
Tensile Strength at break	ASTM D638	MPa	22.6	21.6	19
Elongation	ASTM D638	%	800	800	800
Surface Hardness	ASTM D2240	Shore D	32	30	2
Stiffness	ASTM D747	MPa	49.0	58.8	29
Vicat Softening Point	ASTM D1525	°C	63	68	5
Brittle Point	ASTM D746	°C	< -75	< -75	< -
ESCR *	ASTM D1693	Hr	> 300	> 300	> 3

- The figures presented are typical laboratory averages, only for reference.
- The information is based on our current knowledge, is subjected to continuous updates and is intended to suggest/ recommend product applications and to provide typical data on the related properties. It should not therefore be construed as guaranteeing any specific property of the product. TPC makes no warranty of any kind, expressed or implied, regarding the accuracy of these data.