

Technical Information


TRINSEO™

PLEXIGLAS® V045-100G

Overview

Plexiglas® V045-100G is a thermoplastic acrylic resin formulated for injection molding and extrusion applications. It is characterized by its chemical and heat resistance as well as a high melt flow. Plexiglas® V045-100G has excellent weatherability and optical properties allowing it to excel in applications requiring outdoor stability, high quality surface appearance and/or precision optics. Plexiglas® V045-100G is easy to process due to its exceptional thermal stability, extrusion melt strength, and excellent tool surface reproduction and release properties. Supplemental moldflow simulation data is available upon request. It has excellent resistance to many chemicals including solutions of inorganic acids, alkalis and aliphatic hydrocarbons such as VM&P naphtha and heptane. Additionally, it is virtually unaffected by a wide range of commercial products including many beverages, foodstuffs, detergent solutions and cleaners.

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.19 g/cm ³	1.19 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	2.3 g/10 min	2.3 g/10 min	ASTM D1238
Molding Shrinkage - Flow	2.0E-3 to 6.0E-3 in/in	0.20 to 0.60 %	ASTM D955
Water Absorption (24 hr)	0.30 %	0.30 %	ASTM D570
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	450000 psi	3100 MPa	ASTM D638
Tensile Strength (Break)	10200 psi	70.3 MPa	ASTM D638
Tensile Elongation (Break)	6.0 %	6.0 %	ASTM D638
Flexural Modulus	450000 psi	3100 MPa	ASTM D790
Flexural Strength (Break)	15000 psi	103 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.30 ft-lb/in	16 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (M-Scale)	91	91	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load ¹			ASTM D648
66 psi (0.45 MPa), Annealed	202 °F	94.4 °C	
264 psi (1.8 MPa), Annealed	199 °F	92.8 °C	
Vicat Softening Temperature			
--	217 °F	103 °C	ASTM D1525 ²
--	207 °F	97.2 °C	ASTM D1525 ³
Thermal Conductivity	1.3 Btu-in/hr/ft ² /°F	0.19 W/m/K	ASTM C177
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating	HB	HB	UL 94
Optical	Nominal Value (English)	Nominal Value (SI)	Test Method
Refractive Index ⁴	1.490	1.490	ASTM D542
Light Transmittance (125.0 mil (3175 µm))	92.0 %	92.0 %	ASTM D1003
Haze (125.0 mil (3175 µm))	< 1.00 %	< 1.00 %	ASTM D1003
Additional Information	Nominal Value (English)	Nominal Value (SI)	Test Method
ASTM Classification	PMMA 0131V2	PMMA 0131V2	ASTM D788
Injection	Nominal Value (English)	Nominal Value (SI)	
Drying Temperature	180 to 190 °F	82 to 88 °C	
Drying Time	4.0 hr	4.0 hr	
Suggested Max Moisture	< 0.10 %	< 0.10 %	

Injection	Nominal Value (English)	Nominal Value (SI)
Suggested Shot Size	50 %	50 %
Suggested Max Regrind	20 %	20 %
Rear Temperature	420 °F	216 °C
Middle Temperature	430 °F	221 °C
Front Temperature	440 °F	227 °C
Nozzle Temperature	430 °F	221 °C
Processing (Melt) Temp	< 520 °F	< 271 °C
Mold Temperature	150 to 190 °F	66 to 88 °C
Injection Rate	Moderate	Moderate
Back Pressure	100 psi	0.689 MPa
Screw Speed	50 to 100 rpm	50 to 100 rpm
Screw L/D Ratio	15.0:1.0 to 20.0:1.0	15.0:1.0 to 20.0:1.0
Screw Compression Ratio	2.0:1.0 to 2.5:1.0	2.0:1.0 to 2.5:1.0
Vent Depth	2.0E-3 in	0.051 mm

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

¹ Annealing cycle: 4hrs @ 176°F

² Rate A (50°C/h), Loading 1 (10 N)

³ Rate A (50°C/h), Loading 2 (50 N)

⁴ ND @ 72°F

Technical Information



TRINSEO™

trinseo.com

The principles of Responsible Care® and sustainability influence the production of printed literature for Trinseo PLC and its affiliated companies. As a contribution towards the protection of our environments, Trinseo's printed literature is produced in small quantities and on paper containing recovered/post-consumer fiber and using 100 percent soy-based ink whenever possible.

Product Stewardship

Trinseo and its affiliated companies have a fundamental concern for all who make, distribute, and use their products and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products so that appropriate steps may be taken to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Trinseo products – from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Customers are responsible for reviewing their manufacturing processes and their applications of Trinseo products from the standpoint of human health and environmental quality to ensure that Trinseo products are not used in ways for which they are not suitable. Trinseo personnel are available to answer questions and to provide reasonable technical support. Trinseo product literature, including safety data sheets, should be consulted prior to the use of Trinseo products. Current safety data sheets are available from Trinseo.

No freedom from infringement of any patent owned by Trinseo or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the customer is responsible for determining whether products and the information in this document are appropriate for the customer's use and for ensuring that the customer's workplace and disposal practices are in compliance with applicable legal requirements. Although the information herein is provided in good faith and was believed to be accurate when prepared, Trinseo assumes no obligation or liability for the information in this document.

NOTICE REGARDING MEDICAL APPLICATION RESTRICTIONS

TRINSEO REQUESTS THAT CUSTOMERS REFER TO TRINSEO'S MEDICAL APPLICATION POLICY [HTTP://WWW.TRINSEO.COM/MEDICAL.HTM](http://www.trinseo.com/medical.htm) BEFORE CONSIDERING THE USE OF TRINSEO PRODUCTS IN MEDICAL APPLICATIONS. THE RESTRICTIONS AND DISCLAIMERS SET FORTH IN THAT POLICY ARE INCORPORATED BY REFERENCE.

For more information on products, innovations, expertise, and other services available from Trinseo, visit www.trinseo.com, or in the U.S. contact us at +1-855-TRINSEO (+1-855-874-6736).

DISCLAIMER

TRINSEO MAKES NO WARRANTIES, EITHER EXPRESS OR IMPLIED, IN THIS DOCUMENT; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE (INCLUDING MEDICAL APPLICATIONS) ARE EXPRESSLY EXCLUDED. SINCE THE CONDITIONS AND METHODS OF USE OF THE INFORMATION AND PRODUCTS REFERRED TO ARE BEYOND TRINSEO'S KNOWLEDGE AND CONTROL, TRINSEO DISCLAIMS ANY AND ALL LIABILITY FOR LOSSES OR DAMAGES THAT MAY RESULT FROM RELIANCE ON THE INFORMATION OR USE OF THE PRODUCTS DESCRIBED HEREIN. TRINSEO MAKES NO WARRANTIES, EXPRESS OR IMPLIED, THAT THE USE OF ANY TRINSEO PRODUCT WILL BE FREE FROM ANY INFRINGEMENT CLAIMS.

GENERAL NOTICE

Any photographs of end-use applications in this document represent potential end-use applications but do not necessarily represent current commercial applications, nor do they represent an endorsement by Trinseo of the actual products. Further, these photographs are for illustration purposes only and do not reflect either an endorsement or sponsorship of any other manufacturer for a specific potential end-use product or application, or for Trinseo, or for specific products manufactured by Trinseo. If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Trinseo to change specifications and/or discontinue production, and (4) although Trinseo may from time to time provide samples of such products, Trinseo is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

For additional information not covered by the content of this document or to ensure you have the latest version of this document available, please refer to our website at www.trinseo.com/contact.

Follow us at:



Copyright ©Trinseo (2024) All rights reserved.
™ Trademark of Trinseo S.A. or its affiliates
®Responsible Care is a service mark of the American
Chemistry Council



TRINSEO™