


versalis
www.versalis.eni.com

Technical Data Sheet

info.elastomers@versalis.eni.com

DUTRAL[®]

EP(D)M

OCP 3550

Ethylene - Propylene Copolymer

Dutral[®] OCP 3550 is an Ethylene - Propylene polymer produced by suspension polymerisation using a Ziegler-Natta Catalyst.

A non-staining antioxidant is added during the production process.

Main Properties	Unit	Typical Value
MFI (190 °C / 2,16 Kg)	g/10 mins	2,9
Volatiles content	% wt	0.2 max
Ash content	% wt	0.4 max
Propylene content	% wt	48
SSI	%	35 ⁽¹⁾
KV (100 °C)	cSt	11.2 ⁽¹⁾

⁽¹⁾ 1% wt in eni SN150

Key Features

Dutral[®] elastomers are characterized by excellent resistance to ageing and weathering, good resistance to both high and low temperatures, low permanent set values, good resistance to a large number of chemicals.

Dutral[®] OCP 3550 is a low molecular weight copolymer designed as a viscosity index improver for lubricating oils.

It shows a very good thickening power, good shear stability and superior low temperature behaviour.

Main Applications

Oil viscosity modifier;

Physical Form

Bales wrapped with low melting point, oil dissolvable ethylene vinyl acetate copolymer film, typical bale weight: 20 kg.

Packaging

Cardboard box of 500 kg containing 25 bales wrapped with polyethylene film (1070 x 1270 x h1050 mm).

Storage Conditions

Store in dry and vented areas, avoiding temperatures above 35 °C and direct sunlight.

It is recommended that temperatures above 30 °C be avoided for prolonged storage times in order to not deteriorate the quality of the product and reduce its shelf life.

Shelf life : 36 months.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor liability accepted with respect to the use of such information and data.