


versalis
www.versalis.eni.com

Technical Data Sheet

info.elastomers@versalis.eni.com

DUTRAL[®]

EP(D)M

TER 4047

Ethylene - Propylene - Diene Terpolymer

Dutral[®] TER 4047 is an Ethylene - Propylene - Diene polymer produced by suspension polymerisation using a Ziegler-Natta Catalyst at the Ferrara production facility in Italy.
A non-staining antioxidant is added during the production process.

Main Properties	Unit	Typical Value
Mooney Viscosity ML 1+4(125 °C)	MU	55
Volatiles content	% wt	0.5 max
Ash content	% wt	0.3 max
Propylene content	% wt	40
ENB content	% wt	4.5

Key Features

Dutral[®] elastomers are characterized by excellent resistance to ageing and weathering, good resistance to both high and low temperatures, low permanent set values, good resistance to a large number of chemicals.

Dutral[®] TER 4047 is an amorphous medium-high molecular weight terpolymer of medium diene content.

Dutral[®] TER 4047 based compounds exhibit fast extrusion speed, fast curing, high cure state and excellent low temperature behaviour.

Main Applications

Automotive, mechanical goods, buildings.

Physical Form

Bales wrapped with low melting point polyethylene film; typical bale weight: 25 kg.

Packaging

Cardboard box of 750 kg containing 30 bales (1050 x 1250 x h1050 mm).

Storage Conditions

Store in dry and vented areas, avoiding temperatures above 35 °C and direct sunlight.

It is recommended that temperatures above 30 °C be avoided for prolonged storage times in order to not deteriorate the quality of the product and reduce its shelf life.

Shelf life : 36 months.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor liability accepted with respect to the use of such information and data.