



Technical Data Sheet

Europrene® Latice

XSB LATEX

406

Carboxylated Styrene – Butadiene Copolymer

Europrene® Latice 406 is an aqueous dispersion of a modified carboxylated styrene-butadiene copolymer obtained using synthetic anionic emulsifiers. It contains a non staining antioxidant.

Main Properties	Test Method	Unit	Typical Value
Total solid content	ASTM D 1417	% wt	50
Brookfield Viscosity 20 rpm, 25°C	ASTM D 1417	mPa.s	300
Bound styrene	ASTM D 2775	% wt	40
pH	ASTM D 1417		8.0

Key Features

Europrene® Latice 406 is completely ammonia free. It is a functional polymer with waterproof characteristics. It is designed to provide good binding properties and excellent runnability on high speed impregnation lines.

Main Applications

Europrene® Latice 406 is mainly used for paper saturation (masking tape) when enhanced waterproofing properties are required.

Physical Form

At standard condition (T=25 °C P=1 bar) is liquid, color white or milky white.

Packaging

Europrene® Latice 406 is delivered in road tankers/flexitank (bulk) and IBC (1000 l.).

Storage Conditions

Store in closed vented tanks or in a covered place in sealed packaging, away from sunlight and heat sources, at temperature between +5°C and +40°C. The water dispersion should be stirred before use. The shelf life is 6 months minimum.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information data.

® Registered Trademark

November 2022

technicalmanagement@versalis.eni.com | www.versalis.eni.com