



Technical Data Sheet

Europrene® SSBR

SOL B 1205 BCA Styrene – Butadiene Copolymer Bio-Circular Attributed



Europrene® SOL B 1205 BCA is a solution styrene-butadiene partial block copolymer, polymerized using an alkyl lithium catalyst. A non-staining, BHT and TNPP free antioxidant system is added during the production process.

Sustainability

Bio raw materials can be used in production processes together with traditional raw materials. In order to attribute sustainability characteristics to the final product, Versalis applies the **Mass Balance** approach, an acknowledged methodology that ensures that the sustainability characteristics of the alternative raw material, mixed with traditional naphtha, correspond to those of the final product. BCA products are provided with a **sustainability declaration** indicating the amount of Bio-Circular Attributed component. They guarantee identical performance, quality and properties, as they do not differ in chemical composition and physical-mechanical performance from standard products.

Main Properties	Test Method	Unit	Typical Value
Mooney Viscosity ML 1+4(100 °C)	ASTM D 1646	MU	48
Bound Styrene	Internal Method	% wt	25.5
Block Styrene	Internal Method	% wt	18
Brookfield Viscosity	ASTM D 2983	Cp	1250
Volatile Matter	ASTM D 5668	% wt	0.75 max
Ash	ASTM D 5668	% wt	0.10 max

Key Features

Europrene® SOL B 1205 BCA exhibits a narrow molecular weight distribution that assures excellent performance to adhesives applications. The diblock properties have made this type of rubber an important additive for HIPS preparation in order to modify the morphology. It is well suited for footwear and technical rubber good compounds; advantages include wear resistance, flex life, tear resistance, clear color, excellent processability and appearance of the final product.

Main Applications

Adhesives, bitumen modification, HIPS production, footwear, calendered and extruded articles, sheeting, flooring, carpet underlay.

Physical Form

Water white to cream coloured bales wrapped in easily dispersible polyethylene film.

Packaging

Returnable metal crate, nominal net weight 990 kg; 33 kg bale, 30 bales per crate (1465 x 1150 x H1123 mm).
Wooden crate: nominal net weight 990 kg; 33 kg bale, 30 bales per crate (1490 x 1150 x H975 mm).

Storage Conditions

Stored in a vented, dry area at temperatures between 20°C and 30°C, with no direct sunlight.
Shelf life: 24 months minimum.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge, true and accurate, but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information data.

® Registered Trademark