



Technical Data Sheet

Europrene® SSBR

SOL R 74618T Styrene – Butadiene Copolymer

Europrene® SOL R 74618T is a solution polymerized, oil extended styrene-butadiene random copolymer. The polymer is extended with 37.5 phr of TDAE oil and contains a non-staining antioxidant.

Main Properties	Test Method	Unit	Typical Value
Mooney Viscosity ML 1+4(100 °C)	ASTM D 1646	MU	60
Oil content	ASTM D 5774	% wt	27.3
Bound Styrene	Internal Method	% wt	35
Vinyl content	Internal Method	% wt	58 ⁽¹⁾
Volatile matter	ASTM D 5668	% wt	0.75 max
Tg	Internal Method	°C	- 23

⁽¹⁾ Referred to butadiene portion

Key Features

Europrene® SOL R 74618T is designed to enhance grip and handling maintaining good rolling resistance.

Main Applications

Tyre tread compounds for HP/UHP tyres.

Physical Form

Brown coloured bales wrapped in easily dispersible polyethylene film.

Packaging

Returnable metal crate, nominal net weight 990 kg; 33 kg bale, 30 bales per crate (1465 x 1150 x H1123 mm).
On request available in wooden crate: nominal net weight 990 kg; 33 kg bale, 30 bales per crate (1490 x 1150 x H975 mm).

Storage Conditions

Store in a vented, dry area at temperatures between 20°C and 30°C; with no direct sunlight.
Shelf life: 24 months minimum.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor is any liability accepted with respect to the use of such information data.

® Registered Trademark

November 2022

technicalmanagement@versalis.eni.com | www.versalis.eni.com