

Koblend®



PCA 638

Blend PC-ABS

Provisional data sheet

Koblend® PCA 638 is a high impact, high thermal resistant PC/ABS compound.

Applications

Koblend® PCA 638 is specifically designed for:

- automotive.

Typical processing data

Injection moulding:

- dry for 2 - 4h at 110°C
- melt temperature 240-280°C

Extrusion:

- dry for 2 - 4h at 110°C
- melt temperature 240-280°C

Certification

Storage

- ⚠ Store away from atmospheric agents and direct sunlight, away from sources of heat and light.
- 🕒 The product, if stored correctly, keeps its characteristics for at least fifteen months.

General information

Koblend® PCA 638 is available in different shades:

- natural
- black version (internal code 39064).

For further information, please contact Versalis directly writing to info.styrenics@versalis.eni.com.

Koblend®



PCA 638

Blend PC-ABS

Provisional data sheet

Property	Test Conditions	Test method	Units	Values
General				
Density	-	ISO 1183	g/cm ³	1,13
Rheological				
Melt flow rate	260°C - 5kg	ISO 1133	g/10'	15
Mechanical				
Tensile strain at break	50 mm/min	ISO 527	%	55
Tensile stress at break	50 mm/min	ISO 527	MPa	43
Tensile stress at yield	50 mm/min	ISO 527	MPa	50
Flexural strength	2 mm/min	ISO 178	MPa	74
Rockwell hardness	L/M	ISO 2039/2	-	L 86
Tensile modulus	1 mm/min	ISO 527	MPa	2450
Izod impact strength, notched	-30°C - 4mm	ISO 180/1A	kJ/m ²	20
Izod impact strength, notched	+23°C - 4mm	ISO 180/1A	kJ/m ²	47
Thermal				
Deflection temperature under load (annealed)	0,45 MPa - 120°C/h	ISO 75 B	°C	119
Deflection temperature under load (annealed)	1,82 MPa - 120°C/h	ISO 75 A	°C	102
Vicat softening temperature	50 N - 120°C/h	ISO 306/B 120	°C	125

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted.

Versalis is available to provide the guaranteed values for each product on demand.