

Sinkral®



F 332

ABS Resin

Technical Data Sheet

Sinkral® F 332 is a general purpose injection moulding ABS which combines excellent thermal stability during processing with a good balance between flow and impact characteristics.

Designation: Thermoplastic ISO 2580-ABS 1,MGN,105-15-16-20

Applications

Sinkral® F 332 can be used in a variety of industrial sectors:

- small household appliances
- white goods
- vacuum cleaners
- electrical components
- sanitary
- shoe heels
- compounds.

Typical processing data

Injection moulding:

- pre-drying required at 80°C for 2 - 4 hr in an air circulating oven
- melt temperature 230 - 270°C
- mould temperature 40 - 70°C

Certification

✓ UL 94 ✓ FMVSS 302 ✓ VDA 278 ✓ VDA 277 ✓ VDA 270 ✓ NSF 51

Sinkral® F 332, as supplied in the original packaging, by composition is compliant to some existing regulations on plastic materials intended for food contact.

Storage

- ⓘ Store away from atmospheric agents and direct sunlight, away from sources of heat and light.
- 🕒 The product, if stored correctly, keeps its characteristics for at least fifteen months.

General information

Sinkral® F 332 is available in natural colour.

For further information, please contact Versalis directly writing to info.styrenics@versalis.eni.com.

Sinkral®



F 332

ABS Resin

Technical Data Sheet

Property	Test Conditions	Test method	Units	Values
General				
Water absorption	24h - 23°C	ISO 62	%	0,3
Density	-	ISO 1183	g/cm ³	1,04
Rheological				
Melt flow rate	220°C - 10kg	ISO 1133	g/10'	15
Mechanical				
Strain at yield	50 mm / min	ISO 527	%	3
Tensile stress at yield	50 mm/min	ISO 527	MPa	48
Rockwell hardness	Scala R / R Scale	ISO 2039/2	-	110
Tensile modulus	1 mm/min	ISO 527	MPa	2400
Charpy impact strength, notched	+23°C	ISO 179/1eA	kJ/m ²	16
Izod impact strength, notched	+23°C - 4mm	ISO 180/1A	kJ/m ²	17
Thermal				
Coefficient of linear thermal expansion	-	ISO 11359-2	10 ⁻⁵ /°C	9
Thermal conductivity	-	ASTM C 177	W/(K·m)	0,17
Moulding shrinkage	-	ISO 294/4	%	0,4 ÷ 0,6
Deflection temperature under load (annealed)	1,82 MPa - 120°C/h	ISO 75 A	°C	97
Vicat softening temperature	50 N - 50°C/h	ISO 306/B	°C	103
Flammability				
Flame behaviour	1,5 mm	UL 94	cl.	HB
Glow wire test (GWT)	3 mm	IEC 60695-2-10	°C	650
Electrical				
Dielectric constant (relative permittivity)	1000 Hz secco/dry	IEC 60250	-	3,1
Dissipation factor	1000 Hz secco/dry	IEC 60250	-	15·10E-3
Surface resistivity	secco / dry	IEC 60093	ohm	10E14
Volume resistivity	secco / dry	IEC 60093	ohm·cm	10E15
Dielectric strength	secco / dry	IEC 60243	kV/mm	30

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted.

Versalis is available to provide the guaranteed values for each product on demand.