

Product information

VESTOLIT® E 7012 S

Polyvinyl chloride for paste processing


VESTOLIT E 7012 S is a paste-forming homopolymers suitable for production of low to medium viscosity pastes with pseudo-plastic flow.

The properties of the product is particularly suited to the production of soft to medium chemical foams.

Application	Solid	Foam
Coated fabrics	○	○
Floor coverings		○
Wallpapers, wall coverings	○	●
Canvas coating		
Unsupported layers, films	○	○
Dipping, casting		
Spray coating		

● recommended ○ feasible

E 7012 S/DINP-Ratio



Property	Method	Unit	Value ¹⁾
K value	DIN EN ISO 1628-2	-	67
Viscosity number	DIN EN ISO 1628-2	cm ³ /g	112
Apparent bulk density	DIN EN ISO 60	g/cm ³	0.4
Sieve analysis - retained on 0.063 mm sieve	DIN EN ISO 1624	%	< 1
Water content according to K. Fischer	DIN 53 715	%	≤ 0.4
pH value of the aqueous extract	DIN EN ISO 1264	-	7
Paste viscosity 1.5 /s		Pa s	6
Paste viscosity 45 /s		Pa s	4

1) The figures quoted above are typical values, and do not form part of the specification.

100 parts PVC, 60 parts DINP - measured in a rotary viscometer with a defined shear gap at 25 °C after ageing for 2 hours.

VESTOLIT E 7012 S has both fast expansion and very good foam colour. Foams with a high degree of open cells may be produced over a wide processing range. The slight pseudoelasticity of the

pastes made from VESTOLIT E 7012 S and the resulting excellent recovery of the foam mean the product is used predominantly for manufacture of structural foamed wallpaper.

Version 09.2013

VESTOLIT GmbH • D 45753 Marl • P.O. Box 10 23 60
 Phone: + 49 23 65 / 49 - 05 • Fax: + 49 23 65 / 49 - 40 00 • E-Mail: info@vestolit.de

This information is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third part patent rights in particular, no guarantee of properties in the legal sense is implied. We reserve the right to make any change according to technical progress of further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Reference to trade names used by other trade names by other companies neither recommendation, nor is intended to suggest that similar products could be used. All our business transactions shall exclusively be governed by our General sales Conditions. ® = registered trademark