



Product information

VESTOLIT® P 1300 K

Polyvinyl chloride for thermoplastic processing

VESTOLIT P 1300 K is a processing aid for calendering based on high-molecular weight emulsion (E) PVC. Because of its high molecular weight VESTOLIT P1300 K increases the viscosity of the melt causing a faster plastification and smoother running in the calender nip. The occurrence of flow lines is reduced or avoided altogether.

Application	rigid	flexible
Extrusion		
- Profiles, pipes		
- Profiles, hoses		
- Films/foils, sheets		
Calendering		
- HT films	■	
- Floor coverings		

● recommended ○ feasible ■ Additiv

Property	Method	Unit	Value ¹⁾
K value	DIN EN ISO 1628-2	-	n. m.
Apparent bulk density	DIN EN ISO 60	g/cm ³	0.54
Sieve analysis - retained on 0.063 mm sieve	DIN EN ISO 4610	%	≤ 5
Water content according to K. Fischer	DIN 53 715	%	≤ 0.3

1) The figures quoted above are typical values, and do not form part of the specification.

VESTOLIT P 1300 K is used advantageously in the production of thick film gauges where both the inclusion of air and the tendency to stick to the rollers is reduced. VESTOLIT P 1300 K improves

both slip and anti-blocking properties and serves as de-stapling device for cut to size film. Addition levels are normally 0.5 %. Additions levels of up to approx. 1.5 % will normally not affect transparency.

Version 09.2013

VESTOLIT GmbH • D 45753 Marl • P.O. Box 10 23 60
Phone: + 49 23 65 / 49 - 05 • Fax: + 49 23 65 / 49 - 40 00 • E-Mail: info@vestolit.de

This information is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third part patent rights in particular, no guarantee of properties in the legal sense is implied. We reserve the right to make any change according to technical progress of further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Reference to trade names used by other trade names by other companies neither recommendation, nor is intended to suggest that similar products could be used. All our business transactions shall exclusively be governed by our General sales Conditions. ® = registered trademark