



Product information

VESTOLIT® P 1982 K

Polyvinyl chloride for thermoplastic processing

VESTOLIT P 1982 K is a highly impact resistant, modified PVC for production of light and weather resistant window sections.

Application	rigid	flexible
Extrusion		
- Profiles, pipes	●	
- Films/foils, sheets	○	
- Expanded profiles, sheets		
Blow moulding		
- Bottles, containers		
Injection moulding		
- Injection mouldings		
Calendering		
-HT films		
● recommended ○ feasible ■ Additiv		

Property	Method	Unit	Value ¹⁾
K value	DIN EN ISO 1628-2	-	65
Apparent bulk density	DIN EN ISO 60	g/cm ³	0.62
Sieve analysis - retained on 0.063 mm sieve	DIN EN ISO 4610	%	≥ 90
Sieve analysis - retained on 0.200 mm sieve	DIN EN ISO 4610	%	≤ 10
Acrylate content		%	≥ 6.3
Volatile content	DIN EN ISO 1269	%	≤ 0.3

1) The figures quoted above are typical values, and do not form part of the specification.

VESTOLIT P 1982 K, a polybutyl acrylate / vinyl chloride graft copolymer, is suitable for the production of dry blends corresponding to the moulding

compound PVC-U, EDLP, 082-25-T23 according to ISO 1163 using suitable stabilisers, lubricants and non-fading pigments.

Version 09.2013

VESTOLIT GmbH • D 45753 Marl • P.O. Box 10 23 60
 Phone: + 49 23 65 / 49 - 05 • Fax: + 49 23 65 / 49 - 40 00 • E-Mail: info@vestolit.de

This information is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third part patent rights in particular, no guarantee of properties in the legal sense is implied. We reserve the right to make any change according to technical progress of further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Reference to trade names used by other trade names by other companies neither recommendation, nor is intended to suggest that similar products could be used. All our business transactions shall exclusively be governed by our General sales Conditions. ® = registered trademark