

Product Information



Vinnolit K 221

High molecular weight PVC specialty product for thermoplastic processing

Brief Description

®Vinnolit K 221 is a fine-particle, high molecular weight specialty product used as additive in PVC compounds to texture surfaces.

Raw Material Properties	Typical Value *	Unit	Test method	
			DIN EN ISO	ISO
K-value	not measurable	-	1628-2	1628-2
Apparent bulk density	ca. 0,550	g/ml	60	60
Particle size distribution: Sieve retention R retained on 0,100 mm screen	< 1	%	4610	4610
Volatile matter	< 0,3	%	-	1269

* The values given above are **typical** test results which should be used as a guide only. They do not form the whole or part of a specification or guarantee.

Processing and Applications

Vinnolit K 221 is a fine-particle, free-flowing powder that is added to conventional PVC formulations for rigid, semi-rigid or flexible articles. The required amount of Vinnolit K 221 is generally 3 to 10 phr.

During to the high molecular weight, the original particle shape is nearly unaffected by processing. This results in moulded parts with surface textures similar to those obtained by embossing with sandblasted rollers.

In contrast to mechanical embossing, however, the surface of a moulded part textured with Vinnolit K 221 is also retained during subsequent heating and deforming, such as thermoforming. For injection moulding applications, Vinnolit K 221 functions both as a matting agent as well as a mould release.

The main application areas are films, profiles and injection moulded parts.

®Vinnolit = registered trademark of Vinnolit GmbH & Co. KG, Germany

Product Information

Packaging, Delivery and Storage

The product is supplied in 25-kg bags.

Vinnolit K 221 should be stored dry and away from direct or indirect sources of heat. Please consult the safety data sheet for information about the safety precautions necessary for transport, storage, blending and processing.

General Information

Further processing information and recommendations can be obtained from our Technical Service or our local representatives.

The data and recommendations contained in this product information represent the current state of our knowledge and serve as a guide only to our products and their potential applications. Therefore, no warranty of specific properties of the products mentioned herein nor of their suitability or fitness for a particular purpose is implied.

The information given in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also used. Patent or other proprietary rights of third parties must be observed. The quality of our products is warranted under the terms of our General Conditions of Sale.

Ismaning, January 2004

Vinnolit GmbH & Co. KG
Carl-Zeiss-Ring 25
D-85737 Ismaning
Tel.: +49 89 96103-0
Fax: +49 89 96103-103
www.vinnolit.com