



# ELEVATE® EB525

Ethylene Vinyl Acetate Copolymer

## Applications

- Extrusion coatings and thermal laminations
- Cast film

## Product Description

ELEVATE® EB525 is a 15.0% VA ethylene vinyl acetate copolymer designed for cast film, extrusion coatings, and thermal laminations.

## Typical Physical Properties

| Property <sup>a</sup>     |      | Test Method <sup>b</sup> | Typical Value, Units <sup>c</sup> |
|---------------------------|------|--------------------------|-----------------------------------|
| Melt Index                |      | D 1238                   | 8.0 g/10 min                      |
| Peak Melting Point by DSC |      | D 3418                   | 80°C (176°F)                      |
| Vicat Softening Point     |      | D 1525                   | 66°C (151°F)                      |
| Dart Impact               |      | D 1709                   | 125 g/mil                         |
| Haze                      |      | D 1003                   | 2.0%                              |
| Gloss @ 45°               |      | D 2457                   | 85                                |
| Ultimate Tensile          | M.D. | D 882                    | 3,500 psi                         |
|                           | T.D. | D 882                    | 3,000 psi                         |
| Elongation                | M.D. | D 882                    | 400%                              |
|                           | T.D. | D 882                    | 800%                              |
| 1% Secant Modulus         | M.D. | D 882                    | 10,000 psi                        |
|                           | T.D. | D 882                    | 11,000 psi                        |

<sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

<sup>b</sup> Unless noted otherwise, the test method is ASTM.

<sup>c</sup> Units are in SI or US customary units.

## Notes

Test specimens for cast film: nominal thickness 1.0 mils

## Processing

Melt temperatures of 370°F – 410°F are recommended for ELEVATE® EB525 for cast film extrusion.

## Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

*Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.*

**Westlake Polymers LLC**  
 2801 Post Oak Boulevard, Suite 600  
 Houston, Texas 77056  
 1.800.545.9577  
[www.westlake.com](http://www.westlake.com)