




Phone: 1.610.459.1000
 Phone: 1.800.000.0000
 Fax: 610.459.1084
 490 West Lenni Road
 Lenni, PA 19052 U.S.A.
 Email: info@westlakeplastics.com

Pomalux® CN-P




Pomalux® POMC CN-P (Statically conductive polyoxymethylene copolymer) is a conductive acetal copolymer. It is a carbon powder filled material that offers consistent surface resistivity in the 10ee4 to 10ee6 range. Properties of note include dimensional stability, strength, stiffness, and chemical resistance.

INDUSTRY



Engineering



Semiconductor and ESD

COLORS AVAILABLE



ATTRIBUTES



Wear Resistance



Chemical Resistance



Dielectric Properties



SHAPES

Compression Sheet





Phone: 1.610.459.1000
Phone: 1.800.000.0000
Fax: 610.459.1084
490 West Lenni Road
Lenni, PA 19052 U.S.A.
Email: info@westlakeplastics.com

Pomalux® CN-P

TECHNICAL SPECIFICATIONS

PROPERTY	TEST STANDARD	ENGLISH UNITS	METRIC UNITS
Mechanical			
Flexural Modulus	D790	169 kpsi	1,170 MPa
Flexural Strength - 5%	D790	4,206 psi	29 MPa
Izod Impact, notched	D256	15.36 ft-lb/in	820 J/m
Tensile Elongation @ Break	D638	48.00 %	48.00 %
Tensile Elongation @ Yield	D638	8.40 %	8.40 %
Tensile Modulus	D638	181 kpsi	1,250 MPa
Tensile Strength @ Break	D638	2.3 kpsi	16 MPa
Tensile Strength @ Yield	D638	3 kpsi	21 MPa
Thermal			
HDT @ 264 psi	D648	123 °F	51 °C
Physical			
Moisture Absorption	D570	0.03 %	0.03 %
Specific Gravity	D792	0.95	0.95
Electrical			
Surface Resistivity	D257	3,477 ohm/sq (ft)	1,060 ohm/sq (m)

SIZING



Phone: 1.610.459.1000
 Phone: 1.800.000.0000
 Fax: 610.459.1084
 490 West Lenni Road
 Lenni, PA 19052 U.S.A.
 Email: info@westlakeplastics.com

Pomalux® CN-P

Compression Sheet Sizing

48" Length by 24" Width

0.25" (6.35mm)	0.375" (9.53mm)	0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)
1.50" (38.1mm)	1.75" (44.45mm)	2" (50.8mm)	2.25" (57.15mm)	2.50" (63.5mm)	2.75" (69.85mm)
3" (76.2mm)	3.25" (82.55mm)	3.50" (88.9mm)	3.75" (95.25mm)	4" (101.6mm)	

96" Length by 48" Width

0.25" (6.35mm)	0.375" (9.53mm)	0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)
1.50" (38.1mm)	1.75" (44.45mm)	2" (50.8mm)	2.25" (57.15mm)	2.50" (63.5mm)	2.75" (69.85mm)
3" (76.2mm)	3.25" (82.55mm)	3.50" (88.9mm)	3.75" (95.25mm)	4" (101.6mm)	

120" Length by 48" Width

0.25" (6.35mm)	0.375" (9.53mm)	0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)
1.50" (38.1mm)	1.75" (44.45mm)	2" (50.8mm)	2.25" (57.15mm)	2.50" (63.5mm)	2.75" (69.85mm)
3" (76.2mm)	3.25" (82.55mm)	3.50" (88.9mm)	3.75" (95.25mm)	4" (101.6mm)	

120" Length by 60" Width

0.25" (6.35mm)	0.375" (9.53mm)	0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)
1.50" (38.1mm)	1.75" (44.45mm)	2" (50.8mm)	2.25" (57.15mm)	2.50" (63.5mm)	2.75" (69.85mm)
3" (76.2mm)	3.25" (82.55mm)	3.50" (88.9mm)	3.75" (95.25mm)	4" (101.6mm)	

LAST REVISED: 06/06/2022

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe any patents. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential loss) shall be available to the buyer.

EXCLUSION OF WARRANTIES: THERE ARE NO WARRANTIES AS TO THE MATERIAL DESCRIBED HEREIN, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. ANY VALUES STATED IN SELLER'S LITERATURE ARE TYPICAL PROPERTIES ONLY.