



Phone: 1.610.459.1000
 Phone: 1.800.000.0000
 Fax: 610.459.1084
 490 West Lenni Road
 Lenni, PA 19052 U.S.A.
 Email: info@westlakeplastics.com

Ethylux®



Ethylux® LDPE is a soft, flexible, lightweight plastic material, noted for its low temperature flexibility, toughness, and corrosion resistance. The polymer also has a wide range of appeal for food processing and packaging markets. Ethylux® LDPE has good chemical and impact resistance and is easy to fabricate and form. It is a highly flexible product and is used widely in orthotics and prosthetics, or where mobility without stress fatigue is desired. Ethylux® LDPE is also frequently used in consumer packaging, bags, bottles, and liners.

INDUSTRY



Chemical Process



Engineering

COLORS AVAILABLE



ATTRIBUTES



Impact Resistance



Food Contact



Chemical Resistance



SHAPES

Compression Sheet



Extruded Sheet



Extruded Film





Phone: 1.610.459.1000
 Phone: 1.800.000.0000
 Fax: 610.459.1084
 490 West Lenni Road
 Lenni, PA 19052 U.S.A.
 Email: info@westlakeplastics.com

Ethylux®

TECHNICAL SPECIFICATIONS

PROPERTY	TEST STANDARD	ENGLISH UNITS	METRIC UNITS
Mechanical			
Tensile Elongation @ Break	D638	650.00 %	650.00 %
Tensile Strength @ Break	D638	1.8 kpsi	12.40 MPa

SIZING

Compression Sheet Sizing

48" Length by 24" Width

0.25" (6.35mm)	0.375" (9.53mm)
----------------	-----------------

96" Length by 48" Width

0.25" (6.35mm)	0.375" (9.53mm)	0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)
1.5" (38.1mm)	1.75" (44.45mm)	2" (50.8mm)	2.25" (57.15mm)	2.5" (63.5mm)	2.75" (69.85mm)
3" (76.2mm)	3.25" (82.55mm)	3.50" (88.9mm)	3.75" (95.25mm)	4" (101.6mm)	4.25" (107.95mm)
4.50" (114.3mm)	4.75" (120.65mm)	5" (127mm)	5.25" (133.35mm)	5.50" (139.7mm)	5.75" (146.05mm)
6" (152.4mm)					

120" Length by 48" Width

0.25" (6.35mm)	0.375" (9.53mm)	0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)
1.50" (38.1mm)	1.75" (44.45mm)	2" (50.8mm)	2.25" (57.15mm)	2.50" (63.5mm)	2.75" (69.85mm)
3" (76.2mm)	3.25" (82.55mm)	3.50" (88.9mm)	3.75" (95.25mm)	4" (101.6mm)	4.25" (107.95mm)
4.50" (114.3mm)	4.75" (120.65mm)	5" (127mm)	5.25" (133.35mm)	5.50" (139.7mm)	5.75" (146.05mm)
6" (152.4mm)					



Phone: 1.610.459.1000
 Phone: 1.800.000.0000
 Fax: 610.459.1084
 490 West Lenni Road
 Lenni, PA 19052 U.S.A.
 Email: info@westlakeplastics.com

Ethylux®

120" Length by 60" Width

0.375" (9.53mm)	0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)	1.50" (38.1mm)
1.75" (44.45mm)	2" (50.8mm)	2.25" (57.15mm)	2.50" (63.5mm)	2.75" (69.85mm)	3" (76.2mm)

Extruded Sheet Sizing

96" Length by 48" Width

0.03" (0.76mm)	0.035" (0.89mm)	0.06" (1.52mm)	0.062" (1.57mm)	0.08" (2.03mm)	0.09" (2.29mm)
0.095" (2.41mm)	0.125" (3.18mm)	0.1875" (4.76mm)	0.25" (6.35mm)		

Film Sizing

26" Width

0.002" (0.05mm)	0.003" (0.08mm)	0.004" (0.1mm)	0.005" (0.13mm)	0.01" (0.25mm)	0.02" (0.51mm)
-----------------	-----------------	----------------	-----------------	----------------	----------------

LAST REVISED: 06/01/2022

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe any patents. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential loss) shall be available to the buyer.

EXCLUSION OF WARRANTIES: THERE ARE NO WARRANTIES AS TO THE MATERIAL DESCRIBED HEREIN, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. ANY VALUES STATED IN SELLER'S LITERATURE ARE TYPICAL PROPERTIES ONLY.