



EF1807

Low Density Polyethylene

Applications

- Shrink film
- Frozen food packaging

Product Description

Westlake EF1807 is a fractional melt LDPE resin suggested for film applications that require toughness, such as shrink films and frozen food packaging.

Typical Physical Properties

Property ^a		Test Method ^b	Typical Value, Units ^c
Melt Index		D 1238	0.70 g/10 min
Density		D 4883	921 kg/m ³ (0.921 g/cm ³)
Haze		D 1003	8.3%
Gloss @ 45°		D 2457	68
Dart Impact		D 1709	100 g/mil
Ultimate Tensile	M.D.	D 882	3,600 psi
	T.D.	D 882	2,800 psi
Elongation	M.D.	D 882	250%
	T.D.	D 882	740%
1% Secant Modulus	M.D.	D 882	27,000 psi
	T.D.	D 882	33,000 psi

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Notes

Test specimens for blown film: nominal thickness 1.5 mils; blow up ratio 2.5:1, die gap 50 mils.

Processing

Melt temperatures of 360°F – 400°F are recommended for Westlake EF1807 with blow-up ratios of 2.4:1 or higher.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

Westlake Polymers LLC
2801 Post Oak Boulevard, Suite 600
Houston, Texas 77056
1.800.545.9577
www.westlake.com

05/12/20