

Technical Data Sheet

Applications

- Clarity films

Product Description

Westlake EF612 is an LDPE resin suggested for use in films requiring good clarity and toughness. It has excellent processability, and is an excellent choice as a blend resin with LLDPE in general-purpose clarity packaging applications.

Typical Physical Properties

Property ^a	Test Method ^b	Typical Value, Units ^c
Melt Index (Condition 190°C/2.16 kg)	D 1238	2.50 g/10 min
Density (Base Formulation)	D 1505	920 kg/m ³ (0.920 g/cm ³)
Dart Impact	D 1709	75 g
Haze (Formulated Version)	D 1003	5.3 %
Tensile Strength @ Break	M.D. D 882 T.D. D 882	22.8 MPa (3,300 psi) 15.9 MPa (2,300 psi)
Elongation @ Break	M.D. D 882 T.D. D 882	350 % 680 %
1% Secant Modulus	M.D. D 882 T.D. D 882	172.4 MPa (25,000 psi) 193 MPa (28,000 psi)

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

Notes

Test specimens for blown film: nominal thickness 1.25 mils; blow up ratio 2.5:1, die gap 35 mils.

Processing

Melt temperatures of 360°F – 400°F are recommended for Westlake EF612 with blow-up ratios of 1.5:1 or higher.

Regulatory Compliance

This product has some 21 CFR clearances. Please contact your Westlake Sales Representative for food contact statements.

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given. Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

Westlake Polymers LLC
2801 Post Oak Boulevard, Suite 600
Houston, Texas 77056
1.800.545.9577
www.westlake.com

07/07/22