

Technical Data Sheet

10753

Description/Application

Flame retardant 60C compound suitable for integral non-metallic conduit and general purpose jacket applications.

Properties	Typical Value	Method
Specific Gravity (+/- 0.02)	1.23	ASTM D-792
Hardness Delayed, Shore A (+/- 3)	75	ASTM D-2240
Tensile Strength, psi	2,550	ASTM D-638
Elongation, %	375	ASTM D-638
100% Modulus, psi	1,075	ASTM D-638
Brittle Point, C	-47	ASTM D-746
Oxygen Index, %	24.0	ASTM D-2863
Air Aging: 168 hours @ 100C; 30 mil slab		
Elongation Retention, %	83.0	UL 1581
Recommended Stock Temperature	360 F	

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.

Revision Date: 2/17/2003

P. O. BOX 2729

*

MADISON, MS 39130

PHONE 601/856-8993

axial