

Technical Data Sheet

113B-FR

Description/Application

Non-lead stabilized, 105 C rated injection molding compound. Rated 94Vo at 1.50 mm and 94V1 at 0.58 mm.

Properties	Typical Value	Method
Specific Gravity (+/- 0.02)	1.25	ASTM D-792
Hardness, Shore A (+/- 3)	90	ASTM D-2240
Tensile Strength, psi	2,400	ASTM D-638
Elongation, %	340	ASTM D-638
Oxygen Index, %	24.0	ASTM D-2863

Recognitions and Approval

UL approved through QMFZ2 for 94Vo in all colors at 1.5 mm and 94V1 in all colors at 0.58 mm

Recommended Stock Temperature 350 F

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.

Revision Date: 10/9/2003

P. O. BOX 2729

*

MADISON, MS 39130

PHONE 601/856-8993

axial