

5/25/23, 9:47 AM

Salesforce



VINYL COMPOUNDS

12770 Flexible

PRODUCT DESCRIPTION		
This flexible, non-lead stabilized compound is formulated to provide excellent low-temperature and sunlight resistant properties for a variety of building wire and jacketing applications. This compound is commonly used in CATV applications.		
GENERAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Specific Gravity (+/- 0.02)	1.34	ASTM D-792
Hardness Delayed, Shore A (+/- 3)	77	ASTM D-2240
MECHANICAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Tensile Strength, psi	2200	ASTM D-638
Tensile Strength, MPa	15	ASTM D-638
Elongation, %	350	ASTM D-638
100% Modulus, psi	1100	ASTM D-638
100% Modulus, MPa	8	ASTM D-638
THERMAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Low-Temperature Brittle Point, °C	-44	ASTM D-746
FLAMMABILITY PROPERTIES	TYPICAL VALUE	TEST METHOD
Limited Oxygen Index, %	23	
OTHER PROPERTIES	TYPICAL VALUE	TEST METHOD
Air Aging		10d@100C 30mil plaques
Air Aging Elongation Retention, %	89.3	UL 1581
ADDITIONAL INFORMATION	TYPICAL VALUE	TEST METHOD
Recommended Stock Temperature, °F	360	

Revised Date:10/29/2019

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.