

Technical Data Sheet**13821****Description/Application**

Non-lead stabilized, sunlight resistant, TW insulation compound also recommended for 75C Class 43 applications or outdoor jacket applications.

Properties	Typical Value	Method
Specific Gravity (+/- 0.02)	1.41	ASTM D-792
Hardness Delayed, Shore A (+/- 3)	82	ASTM D-2240
Tensile Strength, psi	2,300	ASTM D-638
Elongation, %	350	ASTM D-638
100% Modulus, psi	1,275	ASTM D-638
Brittle Point, C	-28	ASTM D-746
Oxygen Index, %	26.0	ASTM D-2863
Volume Resistivity, Ohm-cm 23C and 50% RH	6.0 x E+14	ASTM D-257

Recognitions and Approval

UL recognized component for TW and 720 hour sunlight resistant applications.

Recommended Stock Temperature	350 F
-------------------------------	-------

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.

Revision Date: 11/17/2009

P. O. BOX 2729

*

MADISON, MS 39130

PHONE 601/856-8993

