

5/25/23, 9:58 AM

Salesforce



13872

Download as PDF



VINYL COMPOUNDS

13872 Flexible

PRODUCT DESCRIPTION		
This flexible compound is formulated to provide excellent sunlight resistant and weatherable properties for a variety of exterior building wire, appliance wire, and insulation applications that require UL 720, TW, and Class 43 certification. This non-lead stabilized compound can service temperatures up to 75°C.		
GENERAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Specific Gravity (+/- 0.02)	1.34	ASTM D-792
Hardness Delayed, Shore A (+/- 3)	88	ASTM D-2240
MECHANICAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Tensile Strength, psi	2600	ASTM D-638
Tensile Strength, MPa	18	ASTM D-638
Elongation, %	320	ASTM D-638
100% Modulus, psi	1700	ASTM D-638
100% Modulus, MPa	12	ASTM D-638
THERMAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Low-Temperature Brittle Point, °C	-26	ASTM D-746
FLAMMABILITY PROPERTIES	TYPICAL VALUE	TEST METHOD
Limited Oxygen Index, %	25	
OTHER PROPERTIES	TYPICAL VALUE	TEST METHOD
TCF Column Per UL 83	1.1	
ADDITIONAL INFORMATION	TYPICAL VALUE	TEST METHOD
Recommended Stock Temperature, °F	360	

Revised Date:10/29/2019

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.