

## Technical Data Sheet

### 1651 Clear 7002

#### Description/Application

Flexible polyvinyl chloride compound formulated for USP Class VI applications. The compound possesses exceptional clarity.

| Properties                               | Typical Value | Method      |
|------------------------------------------|---------------|-------------|
| Specific Gravity (+/- 0.02)              | 1.20          | ASTM D-792  |
| Hardness Delayed, Shore A (+/- 3)        | 66            | ASTM D-2240 |
| Tensile Strength, psi                    | 2,250         | ASTM D-638  |
| Elongation, %                            | 410           | ASTM D-638  |
| 100% Modulus, psi                        | 850           | ASTM D-638  |
| Melt Flow (g/10 min) @ 175 C and 14910 g | 84.26         | ASTM D-1238 |
| Recommended Stock Temperature            | 335 F         |             |

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.

Revision Date: 5/10/2007

P. O. BOX 2729

\*

MADISON, MS 39130

PHONE 601/856-8993

axial