

5/25/23, 10:43 AM

Salesforce



16882

Download as PDF



VINYL COMPOUNDS

16882 Flexible

PRODUCT DESCRIPTION		
This flexible, non-lead stabilized compound is formulated to provide excellent low- temperature and weatherable properties for a variety of exterior riser, tray cable, building wire, and jacketing applications. This UV and fungal resistant compound can service temperatures up to 90°C and is commonly used to address riser and fiber optic construction concerns.		
GENERAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Specific Gravity (+/- 0.02)	1.35	ASTM D-792
Hardness Delayed, Shore A (+/- 3)	88	ASTM D-2240
MECHANICAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Tensile Strength, psi	2800	ASTM D-638
Tensile Strength, MPa	19	ASTM D-638
Elongation, %	300	ASTM D-638
100% Modulus, psi	1800	ASTM D-638
100% Modulus, MPa	12	ASTM D-638
THERMAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Low-Temperature Brittle Point, °C	-39	ASTM D-746
FLAMMABILITY PROPERTIES	TYPICAL VALUE	TEST METHOD
Limited Oxygen Index, %	30.5	
OTHER PROPERTIES	TYPICAL VALUE	TEST METHOD
Fungal Resistance		
Air Aging		7d@121C 50mil plaques
Air Aging Elongation Retention, %	84.6	UL 1581

Revised Date:10/29/2019

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.