

**TECHNICAL DATA SHEET****Flexible****19751****DESCRIPTION/ APPLICATION**

19751 is a compound formulated for a 105°C maximum service temperature rating recommended for general purpose insulation or jacket applications.

GENERAL PROPERTIES	VALUE	METHOD
Specific Gravity (+/- 0.02)	1.32	ASTM D-792
Hardness Delayed 10 sec, Shore A (+/- 3)	75	ASTM D-2240
MECHANICAL PROPERTIES	VALUE	METHOD
Tensile Strength, psi	1800	ASTM D-638
Elongation, %	330	ASTM D-638
Modulus, psi	850	ASTM D-638
Oxygen Index, %	23	ASTM D-2863
Air Aging: 168 hrs @ 136°C; 30 mil slab		
Elongation Retention, %	85	UL 1581
RECOMMENDED STOCK TEMPERATURE		340°F

Revision Date: 10/06/2015

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.