

Technical Data Sheet

19901

Description/Application

105 C; VW-1 non-lead stabilized insulation with good flexibility. Ideally suited for 1/64 wall (18 AWG and larger). UL approved for TW, THW, THHW applications.

Properties	Typical Value	Method
Specific Gravity (+/- 0.02)	1.32	ASTM D-792
Hardness Delayed, Shore A (+/- 3)	90	ASTM D-2240
Tensile Strength, psi	2,450	ASTM D-638
Elongation, %	330	ASTM D-638
100% Modulus, psi	1,800	ASTM D-638
Brittle Point, C	-24	ASTM D-746
Oxygen Index, %	28.0	ASTM D-2863
Volume Resistivity, Ohm-cm 23C and 50% RH	1.5 x E+15	ASTM D-257
Air Aging: 7 days at 136 C; 30 mil slabs		
Elongation Retention, %	80.1	UL 1581
Oil Aging: 96 hours at 100 C; 30 mil insulation		
Elongation Retention, %	73.0	UL 1581
Recognitions and Approval		
UL Recognized Component for TW, THW, THHW. VW-1 rated		
Recommended Stock Temperature	365 F	

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.

Revision Date: 3/1/2012

P. O. BOX 2729

*

MADISON, MS 39130

PHONE 601/856-8993

axial