

Technical Data Sheet

22902

Description/Application

Non-lead stabilized riser jacket recommended over PVC and FRHDPE primaries. Maximum service temperature rating of 75C.

Properties	Typical Value	Method
Specific Gravity (+/- 0.02)	1.40	ASTM D-792
Hardness Delayed, Shore A (+/- 3)	90	ASTM D-2240
Tensile Strength, psi	2,920	ASTM D-638
Elongation, %	290	ASTM D-638
100% Modulus, psi	1,980	ASTM D-638
Brittle Point, C	-28	ASTM D-746
Oxygen Index, %	32.5	ASTM D-2863
Air Aging: 240 hrs. @ 100 C; 30 mil slabs		
Elongation Retention, %	77.3	UL 1581
Recommended Stock Temperature	370 F	

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.

Revision Date: 5/27/2005

P. O. BOX 2729

*

MADISON, MS 39130

PHONE 601/856-8993

axial