

5/25/23, 12:37 PM

Salesforce



24880

Download as PDF



VINYL COMPOUNDS

24880 Flexible

PRODUCT DESCRIPTION		
This flexible, non-lead stabilized compound is formulated for a variety of tray cable and building wire applications that require a maximum service temperature of 80°C.		
GENERAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Specific Gravity (+/- 0.02)	1.35	ASTM D-792
Hardness Delayed, Shore A (+/- 3)	90	ASTM D-2240
MECHANICAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Tensile Strength, psi	3100	ASTM D-638
Tensile Strength, MPa	21	ASTM D-638
Elongation, %	300	ASTM D-638
100% Modulus, psi	1900	ASTM D-638
100% Modulus, MPa	13	ASTM D-638
ADDITIONAL INFORMATION	TYPICAL VALUE	TEST METHOD
Recommended Stock Temperature, °F	365	
REGULATORY LISTINGS AND CERTIFICATIONS		
RoHS		
NSF 61		

Revised Date:02/16/2021

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.