

**TECHNICAL DATA SHEET****Flexible****28930****DESCRIPTION/ APPLICATION**

28930 is a compound formulated for UV resistance in 105°C FT-4 riser jacket applications.

GENERAL PROPERTIES	VALUE	METHOD
Specific Gravity (+/- 0.02)	1.41	ASTM D-792
Hardness Delayed 10 sec, Shore A (+/- 3)	93	ASTM D-2240
MECHANICAL PROPERTIES	VALUE	METHOD
Tensile Strength, psi	3000	ASTM D-638
Elongation, %	280	ASTM D-638
OTHER PROPERTIES	VALUE	METHOD
Low Temperature Brittle Point, °C	-19.2	ASTM D-746
Oxygen Index, %	33.5	ASTM D-2863
Air Aging: 168 hours @ 136°C; 30 mil slab		
Elongation Retention, %	68.0	UL 1581
RECOMMENDED STOCK TEMPERATURE		380°F

Revision Date: 12/14/2015

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.