

5/25/23, 12:40 PM

Salesforce



4100-58

Download as PDF



VINYL COMPOUNDS

4100-58 Flexible

PRODUCT DESCRIPTION		
This flexible compound is formulated to provide optimized flexibility and ease of processing for a variety of automotive applications that require ISO 6722 certification. This compound can service temperatures up to 100°C and is commonly used in ultra-thin-walled, 0.35 millimeter ISO conductor applications.		
GENERAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Specific Gravity (+/- 0.02)	1.38	ASTM D-792
Hardness Delayed, Shore D (+/- 3)	58	ASTM D-2240
MECHANICAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Tensile Strength, psi	3400	ASTM D-638
Tensile Strength, MPa	23	ASTM D-638
Elongation, %	280	ASTM D-638
100% Modulus, psi	2600	ASTM D-638
100% Modulus, MPa	18	ASTM D-638
THERMAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Low-Temperature Brittle Point, °C	-16	ASTM D-746
ADDITIONAL INFORMATION	TYPICAL VALUE	TEST METHOD
Recommended Stock Temperature, °F	375	
REGULATORY LISTINGS AND CERTIFICATIONS		
RoHS		

Revised Date:10/29/2019

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.