

5/25/23, 12:44 PM

Salesforce



4425

Download as PDF



VINYL COMPOUNDS

4425
Flexible

PRODUCT DESCRIPTION		
This flexible, non-lead stabilized compound is formulated to meet SAE J1128, SAE J1127, SAE 1560, Ford M1L, and Chrysler MS 7889 standards. With a maximum service temperature of 85°C, this compound will provide you with the best solution to a variety of high-speed, T2 automotive applications.		
GENERAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Specific Gravity (+/- 0.02)	1.36	ASTM D-792
Hardness Delayed, Shore D (+/- 3)	42	ASTM D-2240
MECHANICAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Tensile Strength, psi	2900	ASTM D-638
Tensile Strength, MPa	20	ASTM D-638
Elongation, %	300	ASTM D-638
100% Modulus, psi	2100	ASTM D-638
100% Modulus, MPa	14	ASTM D-638
THERMAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Low-Temperature Brittle Point, °C	-25	ASTM D-746
ADDITIONAL INFORMATION	TYPICAL VALUE	TEST METHOD
Recommended Stock Temperature, °F	365	
REGULATORY LISTINGS AND CERTIFICATIONS		
RoHS		

Revised Date:10/29/2019

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.