

Technical Data Sheet**46234A****Description/Application**

Automotive window encapsulation compound

Properties	Typical Value	Method
Specific Gravity (+/- 0.02)	1.20	ASTM D-792
Hardness Delayed, Shore A (+/- 3)	59	ASTM D-2240
Tensile Strength, psi	1,700	ASTM D-638
Elongation, %	390	ASTM D-638

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.

Revision Date: 2/2/2008

P. O. BOX 2729

*

MADISON, MS 39130

PHONE 601/856-8993

axial