

5/26/23, 9:14 AM

Salesforce



7140

Download as PDF



VINYL COMPOUNDS

7140 Rigid

PRODUCT DESCRIPTION		
This rigid, non-phthalate compound is formulated to provide excellent chemical and flame resistance for a variety of exterior extrusion and custom injection molding applications that require NSF 50/61 and UL certifications. This compound is commonly used in applications that require high-impact strength, high-flow, high-gloss, weatherability, and extrudability.		
GENERAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Specific Gravity (+/- 0.02)	1.47	ASTM D-792
Hardness Delayed, Shore D (+/- 3)	83	ASTM D-2240
Hardness Delayed, Rockwell R	112	ASTM D-2240
Cell Classification	15344	ASTM D-1784
MECHANICAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Tensile Yield Strength, psi	6500	ASTM D-638
Tensile Yield Strength, MPa	45	ASTM D-638
Tensile Modulus, psi	380000	ASTM D-638
Tensile Modulus, MPa	2620	ASTM D-638
Flexural Strength, psi	12100	ASTM D-790
Flexural Strength, MPa	83	ASTM D-790
Flexural Modulus, psi	400000	ASTM D-790
Flexural Modulus, MPa	2758	ASTM D-790
1/8" Notched Izod Impact ft-lbs/in at 23°C	15	ASTM D-256
THERMAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Heat Deflection Temp °C at 264 psi/1.8 MPa	72	ASTM D-648
Coefficient of Thermal Expansion 10 ⁻⁵ in/in °F	4	ASTM D-696

Revised Date:10/29/2019

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.