

5/26/23, 9:17 AM

Salesforce



7255J

Download as PDF



VINYL COMPOUNDS

7255J Rigid

PRODUCT DESCRIPTION		
This rigid, non-phthalate compound is formulated to provide excellent chemical and UV resistance for a variety of profile extrusion applications. This compound is commonly used in exterior applications that require weatherability.		
GENERAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Specific Gravity (+/- 0.02)	1.45	ASTM D-792
Cell Classification	14144442	ASTM D-4216
MECHANICAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Tensile Yield Strength, psi	6600	ASTM D-638
Tensile Yield Strength, MPa	46	ASTM D-638
Tensile Modulus, psi	410000	ASTM D-638
Tensile Modulus, MPa	2827	ASTM D-638
Flexural Strength, psi	11800	ASTM D-790
Flexural Strength, MPa	81	ASTM D-790
Flexural Modulus, psi	425000	ASTM D-790
Flexural Modulus, MPa	2930	ASTM D-790
1/8" Notched Izod Impact ft-lbs/in at 23°C	16	ASTM D-256
THERMAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Heat Deflection Temp °C at 264 psi/1.8 MPa	76	ASTM D-648
Coefficient of Thermal Expansion 10 ⁻⁵ in/in °F	3.0	ASTM D-696
ADDITIONAL INFORMATION	TYPICAL VALUE	TEST METHOD
Recommended Melt Temperature, °F	360-385	
REGULATORY LISTINGS AND CERTIFICATIONS		
RoHS		

Revised Date:09/03/2020

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.