

Technical Data Sheet

7690

Description/Application

Migration resistant, highly flexible PVC compound recommended for injection molding applications

Properties	Typical Value	Method
Specific Gravity (+/- 0.02)	1.47	ASTM D-792
Hardness Delayed, Shore A (+/- 3)	69	ASTM D-2240
Tensile Strength, psi	1,000	ASTM D-638
Elongation, %	350	ASTM D-638
100% Modulus, psi	600	ASTM D-638
Recommended Stock Temperature	320 F	

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.

Revision Date: 7/20/2011

P. O. BOX 2729

*

MADISON, MS 39130

PHONE 601/856-8993

axial