

Technical Data Sheet

8490

Description/Application

A general purpose extrusion compound especially formulated for extruded T-moldings, tubings and other shapes where uniform flow through the die is required. Standard colors are black and natural.

Properties	Typical Value	Method
Specific Gravity (+/- 0.02)	1.38	ASTM D-792
Hardness Delayed, Shore D (+/- 3)	49	ASTM D-2240
Tensile Strength, psi	3,000	ASTM D-638
Elongation, %	275	ASTM D-638
100% Modulus, psi	2,350	ASTM D-638
Recommended Stock Temperature	375 F	

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.

Revision Date: 7/25/2003

P. O. BOX 2729

*

MADISON, MS 39130

PHONE 601/856-8993

axial