

## Technical Data Sheet

### 8554

#### Description/Application

General purpose, jelly clear flexible PVC compound recommended for extrusion or molding applications.

| Properties                        | Typical Value | Method      |
|-----------------------------------|---------------|-------------|
| Specific Gravity (+/- 0.02)       | 1.16          | ASTM D-792  |
| Hardness Delayed, Shore A (+/- 3) | 55            | ASTM D-2240 |
| Tensile Strength, psi             | 1,200         | ASTM D-638  |
| Elongation, %                     | 500           | ASTM D-638  |
| 100% Modulus, psi                 | 350           | ASTM D-638  |
| Recommended Stock Temperature     | 320 F         |             |

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.

Revision Date: 10/20/2004

P. O. BOX 2729

\*

MADISON, MS 39130

PHONE 601/856-8993

axial