

Technical Data Sheet

8710

Description/Application

Low gravity extrusion compound with excellent low temperature properties. Designed for use in weatherstrips and flexible gaskets. Excellent for co-extrusion with rigid PVC.

Properties	Typical Value	Method
Specific Gravity (+/- 0.02)	1.28	ASTM D-792
Hardness Delayed, Shore A (+/- 3)	71	ASTM D-2240
Tensile Strength, psi	2,000	ASTM D-638
Elongation, %	400	ASTM D-638
100% Modulus, psi	725	ASTM D-638
Brittle Point, C	-45	ASTM D-746
Recommended Stock Temperature	345 F	

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.

Revision Date: 6/23/2000

P. O. BOX 2729

*

MADISON, MS 39130

PHONE 601/856-8993

axial