

5/26/23, 9:36 AM

Salesforce



8820

Download as PDF



VINYL COMPOUNDS

8820 Flexible

PRODUCT DESCRIPTION		
This flexible, general purpose compound is formulated for a variety of weather strip, screen spline, and flexible gasket applications.		
GENERAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Specific Gravity (+/- 0.02)	1.38	ASTM D-792
Hardness Delayed, Shore A (+/- 3)	82	ASTM D-2240
MECHANICAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Tensile Strength, psi	2200	ASTM D-638
Tensile Strength, MPa	15	ASTM D-638
Elongation, %	300	ASTM D-638
100% Modulus, psi	1400	ASTM D-638
100% Modulus, MPa	10	ASTM D-638
THERMAL PROPERTIES	TYPICAL VALUE	TEST METHOD
Low-Temperature Brittle Point, °C	-22	ASTM D-746
ADDITIONAL INFORMATION	TYPICAL VALUE	TEST METHOD
Recommended Stock Temperature, °F	365	
REGULATORY LISTINGS AND CERTIFICATIONS		
RoHS		

Revised Date:10/29/2019

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under, or recommendation to infringe, any patents.